



735 JETSET™ FINISH CHEMICAL RESISTANCE GUIDE

Chemical Agent	Concentration	Temperature °C/ Temperature °F	Chemical Agent	Concentration	Temperature °C/ Temperature °F
	%			%	
Acetic acid	10	99/210	Ethylene Glycol	All	100/212
Acetic Acid	50	70/158	Fatty Acids	All	100/212
Acetone	10	82/179	Ferric Chloride	All	100/212
Acrylic Acid	25	38/100	Ferric Nitrate	All	100/212
Alum	All	100/212	Ferric Sulfate	All	100/212
Aluminum Chloride	All	100/212	Ferrous Chloride	All	100/212
Aluminum Sulfate	All	100/212	Fertilizer URAN		49/120
Ammonia	All	93/199	Fluoboric Acid	10	100/212
Ammonium Chloride	All	99/210.2	Fluosilicic Acid	10	65/149
Ammonium Hydroxide	1	93/199	Fluosilicic Acid	35	38/100
Ammonium Hydroxide	5	82/180	Fluosilicic Acid	Fumes	82/180
Ammonium Hydroxide	10	77/170	Formaldehyde	25-56	66/151
Ammonium Hydroxide	20	66/150	Formic Acid	10	65/149
Ammonium Hydroxide	29	38/100	Formic Acid	50	43/109
Ammonium Nitrate	All	100/212	Fuel Oil	100	99/210
Ammonium Phosphate	All	99/210	Gasoline - Regular Leaded	100	43/109
Amyl Alcohol	All	99/210	Glycerine	100	100/212
Beer		50/122	Green Liquor (pulp mill)		99/210
Beet Sugar Liquor	All	82/179	Heptane	100	99/210
Benzene Sulfonic Acid	30	99/210	Hexane	100	66/151
Benzoic Acid	All	100/212	Hydraulic Fluid	100	82/180
Black Liquor (pulp mill)	All	99/210	Hydrobromic Acid	18	99/210
Boric Acid	All	100/212	Hydrobromic Acid	48	77/171
Brake Fluid		43/109	Hydrochloric Acid	10	99/210
Brine	All	115/239	Hydrochloric Acid	15	99/210
Brown Stock (pulp mill)		82/180	Hydrochloric Acid	25	66/151
Bunker C Fuel Oil	100	99/210	Hydrochloric Acid	37	43/109
Butyl Cellosolve	100	49/120	Hydrocyanic Acid	10	99/210
Calcium Chloride	Sat'd	100/212	Hydrofluoric Acid	1	52/126
Calcium Hydroxide	All	99/210	Hydrofluoric Acid	10	52/126
Calcium Hypochlorite	All	99/210	Hydrofluoric Acid	20	38/100
Cane Sugar Liquor	All	82/179	Hydrofluosilicic Acid	10	66/151
Capric Acid	All	71/159	Hydrofluosilicic Acid	35	50/122
Caprylic Acid (Octanoic)	All	99/210	Hydrogen Chloride-dry gas	100	100/212
Carbon Dioxide Gas		176/349	Hydrogen Peroxide	5	66/151
Carbon Tetrachloride	100	38/100	Hydrogen Peroxide	30	38/100
Chlorinated Pulp		93/199	Hydrogen Sulfide	All	99/210
Chlorinated Waxes	All	82/180	Hydrogen Sulfide, gas	All	115/239
Chlorinated Gas		99/210	Isobutyl Alcohol	All	52/126
Chlorine Dioxide	Sat'd	71/160	Isopropyl Alcohol	All	50/122
Chlorine Water	All	99/210	Jet Fuel		99/210
Chlorite	50	43/109	Kerosene	100	99/210
Chloroacetic Acid	25	82/1800	Lactic Acid	All	100/212
Chloroacetic Acid	50	65/149	Lead Acetate	All	100/212
Chrome Plating Solution		54/129	Levulinic Acid	All	99/210
Chromic Acid	5	43/109	Lime Slurry	All	99/210
Crude Oil, sour or sweet	100	99/210	Magnesium Chloride	All	100/212
Detergents, Organic	100	82/180	Magnesium Sulfate	All	99/210
Detergents Sulfonated	All	99/210	Maleic Acid	All	99/210
Diesel Fuel	All	99/210	Methyl Alcohol (methanol)	100	27/81
Diethylene Glycol	100	100/212	Milk & Milk Products	All	99/210
Embalming Fluid	All	43/110	Mineral Oils	100	100/212
Epoxydized Soya Bean Oil	All	93/199	Motor Oil	100	99/210
Esters of Fatty Acids	100	82/180	Naphthalene	All	100/212
Ethyl Alcohol (Ethanol)	10	60/140	Nickel Chloride	All	100/212
Ethyl Alcohol (Ethanol)	95-100	49/120	Nickel Nitrate	All	100/212
			Nickel Sulfate	All	100/212

735 JETSET™ FINISH CHEMICAL RESISTANCE GUIDE

Chemical Agent	Concentration %	Temperature °C/ Temperature °F	Chemical Agent	Concentration %	Temperature °C/ Temperature °F
Nickel Sulfate	All	100/212	Sodium Ferricyanide	All	100/212
Nitric Acid	5	79/174	Sodium Hydroxide	1	99/210
Nitric Acid	15	66/151	Sodium Hydroxide	5	71/160
Nitric Acid	35	60/140	Sodium Hydroxide	25	71/160
Nitric Acid	50	43/109	Sodium Hydroxide	50	99/210
Oleic Acid	All	100/212	Sodium Hypochlorite	15	52/126
Oxalic Acid	100	100/212	Sodium Silicate	100	93/199
Paper Mill Effluent	100	65/149	Sodium Sulfide	All	100/212
Perchloroethylene	100	38/100	Sodium Sulfite	All	100/212
Perchloric Acid	30	38/100	Stannic Chloride	All	100/212
Phenol (Carbonic Acid)	5	43/109	Stannous Chloride	All	100/212
Phosphoric Acid	80	99/210	Stearic Acid	All	100/212
Phosphoric Acid Vapor		99/210	Sulphite/Sulphate Liquors		99/210
Phthalic Acid	100	99/210	Sulfonated Animal Fats	100	82/180
Plating Solutions	All	99/210	Sulfur Dioxide wet or dry		121/250
Polyphosphoric Acid	115	99/210	Sulfur Molten		121/250
Potassium Chloride	All	100/212	Sulfuric Acid	25	100/212
Potassium Dichromate	All	100/212	Sulfuric Acid	50	100/212
Potassium Ferricyanide	All	100/212	Sulfuric Acid	70	82/180
Potassium Hydroxide	10	66/151	Sulfuric Acid	75	49/120
Potassium Hydroxide	25	60/140	Sulfuric Acid	fumes	100/212
Potassium Nitrate	All	100/212	Superphosphoric Acid	105	99/210
Potassium Permanganate	All	99/210	Tannic Acid	All	100/212
Propylene Glycol	All	100/212	Tartaric Acid	All	100/212
Sea Water		115/239	Trichloroacetic Acid	50	100/212
Sodium Acetate	All	100/212	Turpentine		66/151
Sodium Carbonate	10	82/180	Urea	All	77/171
Sodium Carbonate	35	71/160	Vegetable Oils	All	100/212
Sodium Chloride	All	100/212	Water, Deionized	All	99/210
Sodium Chlorite	10	71/160	Water, Demineralized		99/210
Sodium Chlorite	50	43/109	Zinc Chloride	All	99/210
Sodium Cyanide	5	100/212	Zinc Cyanide	All	82/180

WARRANTY DISCLAIMER

The information herein is to assist customers in determining whether our products are suitable for their application. Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to the contents and suitability. We warrant that our products will meet our written specifications. Nothing herein shall constitute a warranty expressed or implied, including any warranty of merchantability or fitness, nor is protection from any loss or patent to be inferred. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.