



473
D-TECH™
FINISH COAT
By Imco®

DESCRIPTION

473 D-TECH™ FINISH COAT is a higher solids version of 470 D-TECH™ and is used as the finishing coat over the 470 application. The **470/473** system is a ready-to-use, clear, water-based penetrating sealer system designed for application to the surface of concrete, above or below grade, interior or exterior.

BASIC USES

Brushed, rolled or sprayed on concrete for sealing, hardening, dust proofing, waterproofing and weatherproofing. Protects concrete surfaces from abrasion and freeze-thaw damage and stops water seepage where it is not caused by cracking or other structural failure.

MAJOR ADVANTAGES OF 473 D-TECH™ FINISH COAT

- Increases concrete density and hardness
- Prevents chemical corrosion and physical abrasion of the treated surface
- Effective in reducing freeze-thaw spalling
- Treatment is permanent and does not require subsequent reapplication every few years
- Effective as a negative side waterproofing against a hydrostatic head of over 115 ft/35 m
- Reduces or eliminates efflorescence and leaching in concrete
- Effective barrier (without loss of breathability) of water-vapor emission through concrete
- Solvent-free, odor-free, non-toxic and non-flammable
- Improves the bonding of cementitious toppings, coatings and paints
- Ultra-violet stability
- Treated surface is more resistant to water and de-icing salt intrusion

TECHNICAL AND PRODUCT DATA

D-TECH™ penetrates deeply into the capillary pores of the concrete and crystallizes, becoming part of the concrete itself.

D-TECH™ will not change the appearance of the concrete surface to which it is applied.

D-TECH™ has been tested as a chemical hardener by the Schmidt hammer rebound test with the following results:

10 year old slab			
- untreated	2000 psi (13.8 MPa)	No. of Components	One
- one coat 470	3000 psi (20.7 MPa)	Packaging	20L pails & 200L drum
- two coats	4600 psi (31.7 MPa)	Pot Life	Indefinite
New Pour Treated	4900 psi (33.7 MPa)	Shelf Life	12 months at 5-24°C (41-75°F)
- one coat 470	6000 psi (41.3 MPa)	Clean-up	Water
Flash Point	None		

473
D-TECH™
FINISH COAT
By Imco®

APPLICATION INSTRUCTIONS

Mix D-TECH™ thoroughly before using and keep it agitated during use as the active ingredients are in suspension and will settle. Do not thin in any way.

Fresh Concrete - D-TECH™ is applied to green concrete as soon as the surface water sheen has disappeared and the concrete can be walked upon. On vertical, formed surfaces, D-TECH™ is applied as soon as the forms have been stripped.

Old concrete - Surfaces to be treated should be swept or brushed clean and then tested for absorption by sprinkling water on them. If the water drops bead up and are not readily absorbed by the concrete, the surface must have been previously coated or oiled and it must therefore be cleaned before D-TECH™ application. D-TECH™ must be absorbed into the slab to be effective. Oil or other stains must be removed before applying D-TECH™. Wash the surface with a strong stripper such as a 7:1 solution of muriatic acid and/or a strong detergent such as trisodium phosphate. Rinse thoroughly with water and remove excess water. Puddled water must be removed.

COVERAGE

473 D-TECH™ FINISH COAT is best applied by low pressure spray, although it can be applied with a roller or brush. **473** is normally applied at the rate of 300 square feet per gallon (75 sf/L) as a finish coat over a 470 application. If the application is in one coat, coverage should be about 190 square feet per gallon (50 sf/L). A blooming or whitish deposit sometimes forms on the surface if ponded areas are left to dry. To avoid this blooming effect make sure that D-TECH™ is not allowed to pond on the surface or flush the surface with clear water 30 to 45 minutes after application to remove any ponding residue. If residue remains after drying, brush with a stiff broom and dilute with D-TECH™ to remove if necessary.

SPECIAL HANDLING

Do not spray or allow overspray on glass or aluminum, it causes etching. Any compound sprayed on glass or aluminum should be immediately rinsed off. Do not allow the product to puddle or allow water to stand on the surface immediately after application, it can leave a residue that is difficult to remove. Rinse the job thoroughly after application whenever possible and use lighter coats if necessary. If difficult residue is formed, try scrubbing with a stiff brush and water pressure, and if necessary, dilute the residue with more D-TECH™. Tilt up slabs or other preformed units treated with D-TECH™ and stacked in contact with one another may be bonded together unless a bond breaker is applied, after the D-TECH™, over the surface that will be in contact. D-TECH™ is compatible with most bond breaker systems, check with manufacturer. D-TECH™ should not be applied when ambient temperature is at or below freezing. D-TECH™ should not be applied where rain or other water is running over the surface or while there are puddles of water on the surface or when rain is imminent.

Do not allow D-TECH™ to freeze and do not use any D-TECH™ that has been previously frozen.

SAFETY

Please refer to SDS at www.imcotechnologies.com

WARRANTY DISCLAIMER

The information herein is to assist customers in determining whether our products are suitable for their application. Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to the contents and suitability. We warrant that our products will meet our written specifications. Nothing herein shall constitute a warranty expressed or implied, including any warranty of merchantability or fitness, nor is protection from any loss or patent to be inferred. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.

IMCO TECHNOLOGIES
6254 SKYWAY RD., PO BOX 915
SMITHVILLE, ON. L0R 2A0

TEL 1-877-957-4626
FAX 905-527-0606

info@imcotechnologies.com
www.imcotechnologies.com

IMCO TECHNOLOGIES
3909 Witmer RD, Suite 1014
NIAGARA FALLS, NY 14305